




Øland
Park Allé 366
DK-2605 Brøndby
Tlf. +45 70 20 19 11
Fax +45 44 53 10 51
www.oeland.dk
CVR-nr. 60994013



Analysis information	
Base Material	U.V. Metalized Treated Polypropylene Film
Adhesion	Water based acrylic pressure sensitive adhesive
Peeling Strength With 180#730	1.8-2.8N/cm
Adhesive to Self	Less than 90 gms/cm
Tensile Strength	40-50N/cm
Tensile adhesion	4-5N/cm
Elongation	140%
Water vapour resistance	0.17g/m*2-24 hour at 40°C
Thermal Behaviour	Stable between -20°C to +100°C
Application Temp	-20°C to +40°C (dry surface)
Moisture Vapor Transmission Rate	3.9x10 ⁻⁹ g/Pa s m ²




Main Specification:

-Tape with 1 inch plastic/paper core:

50mm*50m 96rolls/carton.

75mm*50m 64rolls/carton.

100mm*50m 48rolls/carton.



-Tape with normal paper core:

Width: from 20mm to 100mm.(20mm,40mm,48mm,50mm,75mm,100mm)

Length: from 30m to 500m.(30m,50m,100m)

Packaging: 72rolls/carton,75rolls/carton,100rolls/carton.

